

## Lámina Lisa

Lámina Rolada En Caliente Decapada y Sin Decapar							
Peso por hoja en kilogramos							
Espesor			Pies	3 X 8	3 X 10	4 X 8	4 X 10
calibre	mm	pulg	metros	.914 X 2.44	.914 X 3.05	1.22 X 2.44	1.22 X 3.05
a			kg/m <sup>2</sup>	bxc			
3	6.07	0.239	47.65	106.24	132.80	141.66	177.07
4	5.69	0.224	44.67	99.59	124.49	132.79	165.99
5	5.31	0.209	41.68	92.94	116.18	123.92	154.90
6	4.94	0.194	38.78	86.46	108.08	115.29	144.11
7	4.55	0.179	35.72	79.64	99.55	106.19	132.73
8	4.18	0.164	32.81	73.16	91.44	97.55	121.94
9	3.80	0.150	29.83	66.51	83.14	88.68	110.85
10	3.42	0.135	26.85	59.86	74.83	79.81	99.77
11	3.04	0.120	23.86	53.21	66.51	70.95	88.68
12	2.66	0.105	20.88	46.56	58.20	62.08	77.60
13	2.28	0.090	17.90	39.91	49.88	53.21	66.51
14	1.90	0.075	14.92	33.26	41.57	44.34	55.43
15	1.71	0.067	13.42	29.93	37.41	39.91	49.89
16	1.52	0.060	11.93	26.60	33.26	35.47	44.34

Grados Comerciales: SAE 1008, A36

Disponible en Hoja, Cinta o Rollo, en espesores desde calibre 10 hasta calibre 32, en rollo en anchos de 3', 4' y 5'.

Largo a medida, más comercial 6', 8' y 10'.

Lámina Rolada en Frío							
Peso por hoja en kilogramos							
Espesor			Pies	3 X 8	3 X 10	4 X 8	4 X 10
calibre	mm	pulg	metros	.914 X 2.44	.914 X 3.05	1.22 X 2.44	1.22 X 3.05
a			kg/m <sup>2</sup>	bxc			
14	1.90	0.0747	14.92	33.26	41.57	44.34	55.44
16	1.52	0.0598	11.93	26.60	33.26	35.47	44.33
18	1.21	0.0478	9.50	21.18	26.47	28.24	35.30
20	0.91	0.0359	7.14	15.93	19.91	21.24	26.53
22	0.76	0.0299	5.97	13.30	16.63	17.74	22.19
24	0.61	0.0239	4.79	10.68	13.35	14.24	17.80
26	0.45	0.0179	3.53	7.88	9.85	10.50	13.12
28	0.38	0.0149	2.98	6.65	8.31	8.86	11.07
30	0.30	0.0120	2.36	5.25	6.56	7.02	8.77

Nota: El peso es calculado considerando una densidad del acero de 7,850 kg./m.3

Grado acero: Calidad Comercial, troquelado profunda y extraprofundo (ASTM A-1008).

Disponible en Hoja, Cinta o Rollo

